

STOCK NO. 7910046
OCTOBER, 2017

STORMSHIELD ICE AND WATER PROTECTOR

This product consists of a resilient, non-woven glass fiber mat, which is permeated and coated with SBS modified bitumen to a thickness of approx. 1.05 mm (41 mils). This sheet is covered with finely divided mineral matter on its top to provide a non-slip surface while a silicone treated release film, which is easily removed during application, protects its self-adhesive backing. Used primarily for waterproofing purposes under shingled roofs and specifically beneath potential ice dam areas, it can also be installed around vent stacks, dormers, chimneys and other roof-top structures.

CHARACTERISTIC	UNITS	NOMINAL VALUE	SPECIFICATION	TEST METHOD	STANDARD LIMITS
ROLLS PER PALLET:	-	44	-	-	N/A
PALLET SIZE:	cm (in)	132 x 112 (52 x 44)	-	-	-
LENGTH:	m (ft)	19.8 (65)	-	-	± 1%
WIDTH:	mm (in)	914 (36)	-	-	± 3 (1/8)
THICKNESS:	mm (mils)	1.05 (41)	ASTM D1970	ASTM D751	MIN: 1.0 (40)
SELVAGE:	mm (in)	76 (3.0)	-	-	± 6 (1/4)
TENSILE STRENGTH MD: XD:	kN/m (lbf/in)	PASS PASS	ASTM D1970	ASTM D2523	MIN: 4.4 (25)
TEAR STRENGTH MD: XD:	N (lbf)	PASS PASS	ASTM D1970	ASTM D4073	MIN: 89 (20)
THERMAL STABILITY (FLOW AT 70°C):	mm (mils)	PASS	ASTM D1970	ASTM D1204	MAX: 3.0 (118)
COLD FLEX:	°C (°F)	PASS	ASTM D1970	ASTM D1970	MIN: -29 (-20)
WATER VAPOUR PERMEANCE:	ng/Pa·s·m ² (perms)	PASS	ASTM D1970	ASTM E96	≤ 5.7 (≤0.1)
SEALABILITY AROUND NAIL:	-	PASS	ASTM D1970	ASTM D1970	NO WATER PRESENT

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.